

US009944019B2

(12) United States Patent

Falo, Jr. et al.

(54) TIP-LOADED MICRONEEDLE ARRAYS FOR TRANSDERMAL INSERTION

- (71) Applicants: University of Pittsburgh—Of the Commonwealth System of Higher Education, Pittsburgh, PA (US); Carnegie Mellon University, Pittsburgh, PA (US)
- Inventors: Louis D. Falo, Jr., Wexford, PA (US);
 Geza Erdos, Wexford, PA (US); O.
 Burak Ozdoganlar, Sewickley, PA (US)
- (73) Assignees: University of Pittsburgh—Of the Commonwealth System of Higher Education, Pittsburgh, PA (US);
 Carnegie Mellon University, Pittsburgh, PA (US)
- (*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 62 days.
- (21) Appl. No.: 14/398,375
- (22) PCT Filed: May 1, 2013
- (86) PCT No.: PCT/US2013/039084
 § 371 (c)(1),
 (2) Date: Oct. 31, 2014
- (87) PCT Pub. No.: WO2013/166162PCT Pub. Date: Nov. 7, 2013

(65) **Prior Publication Data**

US 2015/0126923 A1 May 7, 2015

Related U.S. Application Data

(60) Provisional application No. 61/641,209, filed on May 1, 2012.

(10) Patent No.: US 9,944,019 B2

(45) **Date of Patent:** Apr. 17, 2018

- (51) Int. Cl. *B29C 67/00* (2017.01) *A61K 9/00* (2006.01) (Continued)

(Continued)

(58) **Field of Classification Search** CPC A61K 9/0021; A61M 2037/0046; A61M 2037/0053; A61M 37/0015; B23C 3/20; B29L 2031/7544

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

5,658,515 A	8/1997	Lee et al.
6,331,266 B1	12/2001	Powell et al.
	(Con	tinued)

FOREIGN PATENT DOCUMENTS

CN IP	1479590 A 2005-35945	3/2004
	(Con	tinued)

OTHER PUBLICATIONS

International Search Report and Written Opinion dated Jan. 14, 2016 by the Australian Patent Office, acting as ISA for PCT App. No. PCT/US2015/059556, 11 pages.

(Continued)

Primary Examiner — Quynh-Nhu H Vu (74) Attorney, Agent, or Firm — Klarquist Sparkman, LLP

(57) ABSTRACT

A method of forming a microneedle array can include forming a microneedle array that has one or more bioactive component. The microneedle array can include a base por-(Continued)



tion and plurality of microneedles extending from the base portion, and the one or more bioactive components are present in a higher concentration in the plurality of microneedles than in the base portion.

14 Claims, 21 Drawing Sheets

(51) Int. Cl.

	A61L 31/16	(2006.01)
	A61M 37/00	(2006.01)
	A61L 31/04	(2006.01)
	B23C 3/20	(2006.01)
	B29L 31/00	(2006.01)
	A61B 17/00	(2006.01)
(52)	U.S. Cl.	

(56) **References Cited**

U.S. PATENT DOCUMENTS

C 451 240	DI	0/2002	C1
6,451,240	DI	9/2002	Sherman et al.
6,511,463	BI	1/2003	wood et al.
6,565,871	B2	5/2003	Roser et al.
6,611,707	B1	8/2003	Prausnitz et al.
6,623,707	B1	9/2003	Addiego et al.
6,652,478	B1	11/2003	Gartstein et al.
6,656,147	B1	12/2003	Gertsek et al.
6.663.820	B2	12/2003	Arias et al.
6.743.211	B1	6/2004	Prausnitz et al.
6 767 211	B2	7/2004	Hall et al
6 881 203	B2	4/2005	Delmore et al
6 800 838	B2	5/2005	Lastovich
6 009 452	D2 D2	6/2005	Elamina at al
6,908,433	D2 D2	0/2003	Varburget al.
6,924,087	BZ	8/2005	Yeshurun et al.
6,931,277	BI	8/2005	Yuzhakov et al.
7,052,268	B2	5/2006	Powell et al.
7,132,054	B1	11/2006	Kravitz et al.
7,211,062	B2	5/2007	Kwon
7,226,439	B2	6/2007	Prausnitz et al.
7,285,113	B2	10/2007	Yeshurun
7,315,758	B2	1/2008	Kwiatkowski et al.
7.316.665	B2	1/2008	Laurent et al.
7.332.197	B2	2/2008	Wood et al.
7 364 568	B2	4/2008	Angel et al
7 416 541	B2	8/2008	Vuzbakov et al
7 420 333	B2	0/2008	Chiou et al
7,427,555	D2 D2	3/2008	Vu et al
7,497,980	D2 D2	3/2009	Au et al.
7,500,050	BZ D2	7/2009	Golubovic-Liakopoulos et al.
7,578,954	B2	8/2009	Gartstein et al.
7,588,552	B2	9/2009	Yeshurun et al.
7,591,806	B2	9/2009	Xu
7,648,484	B2	1/2010	Yeshurun et al.
7,651,475	B2	1/2010	Angel et al.
7,658,728	B2	2/2010	Yuzhakov
7,699,819	B2	4/2010	Yeung et al.
7,731,968	B2	6/2010	Mikszta et al.
D619.245	S	7/2010	Moga et al.
7.753,888	B2	7/2010	Mukeriee et al.
7 763 203	B2	7/2010	Arias et al
7 785 301	B2	8/2010	Yuzhakov
7 846 488	B_2	12/2010	Johnson et al
7 850 657	B2	12/2010	Vachurun at al
7,030,037	D2 с	5/2011	Maga at al
0038,334	ა ნე	3/2011	Woga et al. V an doll
8,052,633	В2 D2	11/2011	Kendall
8,057,842	B2	11/2011	Choi et al.
8,062,573	B2	11/2011	Kwon
8,062,835	B2	11/2011	Tomono

8,088,321 8,101,114	B2 B2 *	1/2012 1/2012	Ferguson et al. Park A61M 37/0015
0.105.500	Da	2/2012	264/442
8,137,736	B2 B2	3/2012 4/2012	Zhu et al. Gonnelli et al.
8,167,852	B2	5/2012	Quan et al.
8,172,815	B2	5/2012	Down et al.
8,192,787	B2 B2	6/2012	Kirby Gartstein et al
8,236,368	B2 B2	8/2012	Jung et al.
8,246,582	B2	8/2012	Angel et al.
8,246,893	B2	8/2012	Ferguson et al.
8,250,729	В2 В2	8/2012 9/2012	Prausnitz et al
8,267,889	B2	9/2012	Cantor et al.
8,328,757	B2	12/2012	Beebe et al.
8,353,861	B2 B2	1/2013	Tobinaga et al. Scholten et al
8,361,037	B2 B2	1/2013	Gonnelli
8,366,677	B2	2/2013	Kaspar et al.
8,376,984	B2	2/2013	James
8,402,629	В2 В2	3/2013	Lee et al. Yuzhakov
8,414,959	B2	4/2013	Hye-Ok et al.
8,419,708	B2	4/2013	Tokumoto et al.
8,444,622	B2	5/2013	Eckhoff et al.
8,449,807	B2 B2	6/2013	Yeshurun et al
8,491,534	B2	7/2013	Takada
8,506,530	B2	8/2013	Laermer et al.
8,506,980	B2	8/2013	Takada Jung et al
8,545,741	B2 B2	10/2013	Chang et al.
8,554,317	B2	10/2013	Duan
8,560,059	B2	10/2013	Hoarau et al.
8,579,862	B2 B2	11/2013	Kobayashi et al.
8,636,696	B2	1/2014	Ross et al.
8,637,136	B2	1/2014	Ferguson et al.
8,671,544	B2	3/2014	Xu et al.
8,696,637	B2 B2	4/2014	Koss Terahara et al
8,708,966	B2	4/2014	Allen et al.
8,734,697	B2	5/2014	Chen et al.
8,741,377	B2 B2	6/2014	Choi et al. Torobara et al
8,758,298	B2 B2	6/2014	Cantor et al.
8,771,781	B2	7/2014	Tokumoto et al.
8,784,368	B2	7/2014	Eckhoff et al.
8,784,373	B2 B2	7/2014	Cole et al
8,784,384	B2	7/2014	Boyden et al.
8,784,385	B2	7/2014	Boyden et al.
8,784,860	B2	7/2014	Falotico et al.
8,785,400	B2 B2	7/2014	Levetan et al. Della Rocca et al
8.788.211	B2	7/2014	Bovden et al.
8,788,212	B2	7/2014	Boyden et al.
8,790,257	B2	7/2014	Libbus et al.
8,790,259	B2	7/2014	Katra et al.
8,790,038	Б2 В2	7/2014	Ligarini et al. Hsu et al
8.791.107	B2	7/2014	Chang et al.
8,793,075	B2	8/2014	Boyden et al.
8,795,174	B2	8/2014	Manicka et al.
8,795,201	B2	8/2014	Escutia et al.
8,795,230	Б2 В2	8/2014	Kadamus et al
8,795,259	$\tilde{B2}$	8/2014	Beebe et al.
8,796,436	B2	8/2014	Manoharan et al.
8,798,722	B2	8/2014	Rylander et al.
8,798,932	B2 B2	8/2014	Boyden et al.
6,796,933 8,821,446	ы2 В2	0/2014 9/2014	Trautman et al.
8,821,779	B2	9/2014	Ferguson et al.
8,834,423	B2	9/2014	Falo, Jr.
2002/0082543	Al*	6/2002	Park A61B 5/1411 604/21

(56) **References Cited**

U.S. PATENT DOCUMENTS

2002/0193729	A1 *	12/2002	Cormier A61B 17/205
			604/272
2002/0198509	A1	12/2002	Mikszta et al.
2004/0058882	A1	3/2004	Eriksson et al.
2005/0049549	A1*	3/2005	Wong A61B 10/0064
			604/46
2005/0065463	A1	3/2005	Tobinaga et al.
2005/0089553	A1	4/2005	Cormier et al.
2005/0251088	A1*	11/2005	Kwon A61M 37/0015
			604/60
2007/0161964	A1	7/2007	Yuzhakov
2007/0260201	A1*	11/2007	Prausnitz A61F 9/0017
			604/272
2008/0009763	A1	1/2008	Chiou et al.
2008/0208134	A1	8/2008	Tomono
2008/0213461	A1	9/2008	Gill et al.
2008/0221532	A1	9/2008	Ogawa
2008/0269685	A1 $*$	10/2008	Singh A61K 9/0021
			604/173
2009/0054842	A1*	2/2009	Yeshurun A61M 37/0015
			604/173
2010/0042137	A1*	2/2010	Oronsky A61M 37/0015
			606/204
2010/0228203	A1	9/2010	Ouan et al.
2011/0046575	A1*	2/2011	Takada A61K 9/0021
			604/265
2011/0098651	A1*	4/2011	Falo, Jr A61M 37/0015
			604/173
2011/0172605	A1*	7/2011	Berenschot A61M 37/0015
			604/173
2011/0230736	A1	9/2011	Tepper et al.
2012/0078189	AI	3/2012	Ogawa et al.
2012/0123341	A1*	5/2012	Birchall A61K 9/0021
	-		604/173
			001175

2012/0265145 A1*	10/2012	Mefti A61M 37/0015
2013/0072902 A1*	3/2013	604/173 Takada A61M 37/0015
2014/0066942 41*	2/2014	604/506 Zhann A 61K 0/0021
2014/0066843 A1*	3/2014	Znang A61K 9/0021 604/46
2014/0142541 A1	5/2014	Yan et al.
2015/0030642 A1*	1/2015	Wu A61K 9/0021
		424/400

FOREIGN PATENT DOCUMENTS

JP	2011-224332	11/2011
WO	WO 2009-004995	1/2009
WO	WO 2009/009004	1/2009
WO	WO 2009/040548	4/2009
WO	WO 2009/081122	7/2009
WO	WO 2010/022252	2/2010
WO	WO 2010/071918	7/2010
WO	WO 2010/141377	12/2010
WO	WO 2012/054582	4/2012
WO	WO 2012/153266	11/2012
WO	WO 2013/166162	11/2013

OTHER PUBLICATIONS

European Search Report dated Mar. 10, 2016 by the European Patent Office, for EPC App. No. 13784192.0, 14 pages.

Office Action, dated Sep. 14, 2017, for corresponding Japanese Patent Application No. 2015-510434, no English-language translation, 4 pages.

Office Action, dated Oct. 31, 2017, in corresponding Chinese Patent Application No. 201380031604.6, with English-language translation, 18 pages.

* cited by examiner

FIG. 1



FIG. 2



FIG. 3A

FIG. 3B



FIG. 4A





























FIG. 9









FIG. 12A







FIG. 13

FIG. 14































U.S. Patent





























FIG. 33



FIG. 35





CTL (SIV_{n=239}gag_{76.84})





FIG. 38

FIG. 39



FIG. 40



TIP-LOADED MICRONEEDLE ARRAYS FOR TRANSDERMAL INSERTION

RELATED APPLICATIONS

This is the U.S. National Stage of International Application No. PCT/US2013/039084, filed May 1, 2013, which was published in English under PCT Article 21(2), which in turn claims the benefit of U.S. Provisional Application No. 61/641,209, filed May 1, 2012. The provisional application is incorporated by reference herein in its entirety.

ACKNOWLEDGMENT OF GOVERNMENT SUPPORT

This invention was made with government support under grant numbers EB012776, AI076060, and CA121973 awarded by the National Institutes of Health. The government has certain rights in the invention.

FIELD

The disclosure pertains to systems and methods for transdermal drug delivery, and, in particular, to systems and 25 methods for making and using dissolvable microneedle arrays.

BACKGROUND

The remarkable physical barrier function of the skin poses a significant challenge to transdermal drug delivery. To address this challenge, a variety of microneedle-array based drug delivery devices have been developed. For example, one conventional method employs solid or hollow 35 microneedles arrays with no active component. Such microneedle arrays can pre-condition the skin by piercing the stratum corneum and the upper layer of epidermis to enhance percutaneous drug penetration prior to topical application of a biologic-carrier or a traditional patch. This method has been shown to significantly increase the skin's permeability; however, this method provides only limited ability to control the dosage and quantity of delivered drugs or vaccine.

Another conventional method uses solid microneedles that are surface-coated with a drug. Although this method provides somewhat better dosage control, it greatly limits the quantity of drug delivered. This shortcoming has limited the widespread application of this approach and precludes, 50 for example, the simultaneous delivery of optimal quantities of combinations of antigens and/or adjuvant in vaccine applications.

Another conventional method involves using hollow microneedles attached to a reservoir of biologics. The 55 microneedle arrays fabricated using layering and spatial syringe needle-type characteristics of these arrays can significantly increase the speed and precision of delivery, as well as the quantity of the delivered cargo. However, complex fabrication procedures and specialized application settings limit the applicability of such reservoir-based 60 microneedle arrays.

Yet another conventional method involves using solid microneedle arrays that are biodegradable and dissolvable. Current fabrication approaches for dissolvable polymerbased microneedles generally use microcasting processes. 65 However, such conventional processes are limited in the active components that can be embedded into the array and

are also wasteful in that they require that the active components be homogenously embedded in the microneedles and their support structures.

Accordingly, although transdermal delivery of biologics using microneedle-array based devices offers attractive theoretical advantages over prevailing oral and needle-based drug delivery methods, considerable practical limitations exist in the design and fabrication associated with microneedle arrays constructed using conventional processes.

SUMMARY

The systems and methods disclosed herein include cuta-15 neous delivery platforms based on dissolvable microneedle arrays that can provide efficient, precise, and reproducible delivery of biologically active molecules to human skin. The microneedle array delivery platforms can be used to deliver a broad range of bioactive components to a patient.

The foregoing and other objects, features, and advantages of the disclosed embodiments will become more apparent from the following detailed description, which proceeds with reference to the accompanying figures.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 illustrates exemplary microneedles and their dimensions.

FIG. 2 illustrates an exemplary microneedle array and its 30 dimensions.

FIGS. 3A and 3B illustrate exemplary microneedles with tip-loaded active components.

FIGS. 4A and 4B illustrate exemplary microneedles with tip-loaded active components.

FIGS. 5A and 5B illustrate exemplary microneedles with tip-loaded active components.

FIGS. 6A and 6B illustrate exemplary microneedles with tip-loaded active components.

FIG. 7 illustrates a miniature precision-micromilling system used for fabricating microneedle mastermolds.

FIG. 8 is an SEM image of a micromilled mastermold with pyramidal needles.

FIG. 9 is an SEM image of a pyramidal production mold. FIG. 10 is an SEM image of an enlarged segment of the production mold, illustrating a pyramidal needle molding well in the center of the image.

FIGS. 11A-11D illustrate exemplary CMC-solids and embedded active components.

FIGS. 12A-12B illustrate exemplary CMC-solids and embedded active components.

FIG. 13 is a schematic illustration of exemplary vertical multi-layered deposition structures and methods of fabricating the same.

FIG. 14 is a schematic illustration of exemplary distribution techniques of embedded active components.

FIG. 15 is a schematic illustration of exemplary microneedle arrays fabricated in a spatially controlled manner.

FIG. 16A is an SEM image of a plurality of pyramidaltype molded microneedles.

FIG. 16B is an SEM image of a single pyramidal-type molded microneedle.

FIG. 17 is an SEM image of a pillar type molded microneedle.

FIG. 18 is a micrograph of pyramidal type molded microneedles.

25

30

40

55

FIG. **19** is a micrograph of pillar type molded microneedles.

FIG. **20** illustrates various microneedle geometries that can be formed using micromilled mastermolds or by direct micromilling of a block of material.

FIG. **21** illustrates a test apparatus for performing failure and piercing tests.

FIG. **22** illustrates force-displacement curves for pillar type microneedles (left) and pyramidal type microneedles (right).

FIG. **23** illustrates a finite elements model of microneedle deflections for pillar type microneedles (left) and pyramidal type microneedles (right).

FIG. **24** show various stereo micrographs of the penetration of pyramidal (A, C, E) and pillar (B, D, F) type ¹⁵ microneedles in skin explants.

FIGS. **25**A, **25**B, and **25**C illustrate the effectiveness of microneedle arrays in penetrating skin explants.

FIGS. **26**A and **26**B illustrate in vivo delivery of particulates to the skin draining lymph nodes of microneedle array ²⁰ immunized mice.

FIG. **27** is a bar graph showing immunogenicity of microneedle delivered model antigens.

FIG. **28** is a bar graph showing the stability of the active cargo of CMC-microneedle arrays in storage.

FIGS. **29**A and **29**B show induction of apoptosis in epidermal cells that have been delivered Cytoxan® (cyclophosphamide) through a microneedle array.

FIG. **30** illustrates a microneedle geometry that can be formed by direct micromilling of a block of material.

FIG. **31** is a stereo microscopic image of a direct-fabricated solid CMC-microneedle array.

FIG. **32** is a stereo microscopic image of a portion of the microneedle array of FIG. **31**.

FIG. **33** is a schematic cross-sectional view of a casting-³⁵ mold assembly for creating a block or sheet of material for direct micromilling.

FIG. **34** is a schematic cross-sectional view of a drying apparatus that can be used to dry a block or sheet of material for direct micromilling.

FIG. **35** is a flow cytometry analysis of GFP expressing target 293T cells.

FIG. **36** illustrates the stability of microneedle embedded viruses after a number of days in storage.

FIG. **37** illustrates the expression and immunogenicity of ⁴⁵ microneedle array delivered adenovectors.

FIG. **38** illustrates an applicator for microneedle insertion into target tissue.

FIG. **39** illustrates applicator head designs for use with the applicator shown in FIG. **38**.

FIG. **40** is a schematic view of dimensional movement of an applicator head.

DETAILED DESCRIPTION

The following description is exemplary in nature and is not intended to limit the scope, applicability, or configuration of the disclosed embodiments in any way. Various changes to the described embodiment may be made in the function and arrangement of the elements described herein 60 without departing from the scope of the disclosure.

As used in this application and in the claims, the singular forms "a," "an," and "the" include the plural forms unless the context clearly dictates otherwise. Additionally, the term "includes" means "comprises." As used herein, the terms 65 "biologic," "active component," "bioactive component," "bioactive material," or "cargo" refer to pharmaceutically

active agents, such as analgesic agents, anesthetic agents, anti-asthmatic agents, antibiotics, anti-depressant agents, anti-diabetic agents, anti-fungal agents, anti-hypertensive agents, anti-inflammatory agents, anti-neoplastic agents, anxiolytic agents, enzymatically active agents, nucleic acid constructs, immunostimulating agents, immunosuppressive agents, vaccines, and the like. The bioactive material can comprise dissoluble materials, insoluble but dispersible materials, natural or formulated macro, micro and nano particulates, and/or mixtures of two or more of dissoluble, dispersible insoluble materials and natural and/or formulated macro, micro and nano particulates.

As used herein, the term "pre-formed" means that a structure or element is made, constructed, and/or formed into a particular shape or configuration prior to use. Accordingly, the shape or configuration of a pre-formed microneedle array is the shape or configuration of that microneedle array prior to insertion of one or more of the microneedles of the microneedle array into the patient.

Although the operations of exemplary embodiments of the disclosed method may be described in a particular, sequential order for convenient presentation, it should be understood that disclosed embodiments can encompass an order of operations other than the particular, sequential order disclosed. For example, operations described sequentially may in some cases be rearranged or performed concurrently. Further, descriptions and disclosures provided in association with one particular embodiment are not limited to that embodiment, and may be applied to any embodiment disclosed.

Moreover, for the sake of simplicity, the attached figures may not show the various ways (readily discernable, based on this disclosure, by one of ordinary skill in the art) in which the disclosed system, method, and apparatus can be used in combination with other systems, methods, and apparatuses. Additionally, the description sometimes uses terms such as "produce" and "provide" to describe the disclosed method. These terms are high-level abstractions of the actual operations that can be performed. The actual operations that correspond to these terms can vary depending on the particular implementation and are, based on this disclosure, readily discernible by one of ordinary skill in the art.

Tip-Loaded Microneedle Arrays

Dissolvable microneedle arrays enable efficient and safe drug and vaccine delivery to the skin and mucosal surfaces. However, inefficient drug delivery can result from the homogenous nature of conventional microneedle array fabrication. Although the drugs or other cargo that is to be delivered to the patient are generally incorporated into the entire microneedle array matrix, in practice only the microneedles enter the skin and therefore, only cargo contained in the volume of the individual needles is deliverable. Accordingly, the vast majority of the drugs or other cargo that is localized in the non-needle components (e.g., the supporting structure of the array) is never delivered to the patient and is generally discarded as waste.

FIGS. 1 and 2 illustrate exemplary dimensions of microneedles and microneedle arrays. Based on the illustrative sizes shown in FIGS. 1 and 2, a microneedle array that comprises an active component homogenously distributed throughout the array exhibits active component waste of greater than 40 percent. For example, if the entire area of the array is 61 mm^2 and the microneedle array area is 36 mm^2 , then the percent utilization of the active component is less than 60 percent. Although the dimensions reflected in FIGS. 1 and 2 illustrate a particular size array and shape of

Ļ

microneedles, it should be understood that similar waste is present in any other size microneedle array in which the active component is homogenously distributed throughout the array, regardless of the size of the array or the shape of the microneedles involved.

The systems and methods described herein provide novel microneedle array fabrication technology that utilizes a fully-dissolvable microneedle array substrate and unique microneedle geometries that enable effective delivery of a broad range of active components, including a broad range 10 of protein and/or small molecule medicines and vaccines.

As described in more detail herein, in some embodiments, this technology can also uniquely enable the simultaneous co-delivery of multiple chemically distinct agents for polyfunctional drug delivery. Examples of the utility of these 15 devices include, for example, (1) simultaneous delivery of multiple antigens and adjuvants to generate a polyvalent immune response relevant to infectious disease prevention and cancer therapy, (2) co-delivery of chemotherapeutic agents, immune stimulators, adjuvants, and antigens to 20 enable simultaneous adjunct tumor therapies, and (3) localized skin delivery of multiple therapeutic agents without systemic exposure for the treatment of a wide variety of skin diseases.

In some embodiments, the systems and method disclosed 25 herein relate to a novel fabrication technology that enables various active components to be incorporated into the needle tips. Thus, by localizing the active components in this manner, the remainder of the microneedle array volume can be prepared using less expensive matrix material that is 30 non-active and generally regarded as safe. The net result is greatly improved efficiency of drug delivery based on (1) reduced waste of non-deliverable active components incorporated into the non-needle portions of the microneedle array, and (2) higher drug concentration in the skin pen- 35 etrating needle tips. This technological advance results in dramatically improved economic feasibility proportional to the cost of drug cargo, and increased effective cargo delivery capacity per needle of these novel microneedle arrays.

FIGS. 3A, 3B, 4A, and 4B illustrate various embodiments 40 of microneedle arrays wherein the active component is concentrated in the microneedle tips of the respective arrays. Thus, in contrast to conventional microneedle arrays, the active component is not present at even concentration throughout the microneedle array since there is little or no 45 active component present in the supporting base structure. In addition, in some embodiments (as shown, for example, in FIGS. 3A, 3B, 4A, and 4B), not only is there little or no active component in the supporting structures, the location of the active component is concentrated in the upper half of 50 the individual microneedles in the array.

FIGS. 5A and 5B illustrate exemplary images of microneedles of a microneedle array that contains active component concentrated in the upper half of the individual microneedles. The active component is illustrated as fluo- 55 rescent particles that are concentrated in the tip of the microneedle, with the tip being defined by an area of the microneedle that extends from a base portion in a narrowing and/or tapered manner. The base portion, in turn, extends from the supporting structure of the array.

FIGS. 6A and 6B illustrate additional exemplary images of microneedles of microneedle arrays that contain active components concentrated in the upper half of the individual microneedles. In FIG. 6A, the active component, which is concentrated in the tip of the microneedles, is BSA-FITC. In 65 FIG. 6B, the active component, which is also concentrated in the tip of the microneedles, is OVA-FITC.

6

As noted above, in some embodiments, individual microneedles can comprise active components only in the upper half of the microneedle. In other embodiments, individual microneedles can comprise active components only in the tips or in a narrowing portion near the tip of the microneedle. In still other embodiments, individual needles can comprise active components throughout the entire microneedle portion that extends from the supporting structure.

The following embodiments describe various exemplary methods for fabricating microneedle arrays with one or more active component concentrated in the upper halves and/or tips of microneedles in respective microneedle arrays.

Microneedle Arrays Fabricated by Sequential Micro-Molding and Spin-Drying Methods

The following steps describe an exemplary method of fabricating microneedle arrays using sequential micro-molding and spin-drying. Active components/cargo can be prepared at a desired useful concentration in a compatible solvent. As described herein, the solvents of the active component(s) can be cargo specific and can comprise a broad range of liquids, including for example, water, organic polar, and/or apolar liquids. Examples of active components are discussed in more detail below and various information about those active components, including tested and maximum loading capacity of various microneedle arrays are also discussed in more detail below.

If desired, multiple loading cycles can be performed to achieve higher active cargo loads as necessary for specific applications. In addition, multiple active cargos can be loaded in a single loading cycle as a complex solution, or as single solutions in multiple cycles (e.g., repeating the loading cycle described below) as per specific cargo-compatibility requirements of individual cargos. Also, particulate cargos (including those with nano- and micro-sized geometries) can be prepared as suspensions at the desired particle number/volume density.

Example 1

a) As described in more detail below in the micromilling embodiments, an active cargo's working stock solution/ suspension can be applied to the surface of microneedle array production molds at, for example, about 40 μ l per cm² surface area.

b) The microneedle array production molds with active cargo(s) can be centrifuged at 4500 rpm for 10 minutes to fill the microneedle array production molds needles with the working cargo stock.

c) The excess cargo solution/suspension can be removed and the surface of the microneedle array production molds, washed with 100 μ l phosphate buffer saline (PBS) per cm² mold-surface area, or with the solvent used for the preparation of the active cargo's working stock.

d) The microneedle array production molds containing the active cargo stock solution/suspension in the needle's cavity can be spin-dried at 3500 rpm for 30 minutes at the required temperature with continues purging gas flow through the centrifuge at 0-50 L/min to facilitate concentration of the drying active cargo(s) in the needle-tips. The purging gas can be introduced into the centrifuge chamber through tubular inlets. Moisture content can be reduced using a dehumidifier tempered to the required temperature with recirculation into the centrifuge chamber. The purging gas can be air, nitrogen, carbon dioxide or another inert or active

60

gas as required for specific cargo(s). The flow rate is measured by flow-meters and controlled by a circulating pump device.

e) 100 μ l 20% CMC90 hydrogel in H2O can be added to the surface microneedle array production molds' per cm² microneedle array production molds-area to load the structural component of the microneedle array device.

f) The microneedle array production molds can be centrifuged at 4500 rpm for 10 min at the required temperature without purging gas exchange in the centrifuge chamber to 10 fill up the microneedle array production molds needle cavities with the CMC90 hydrogel. This can be followed by a 30 min incubation period to enable rehydration of the active cargo(s) previously deposited in the microneedle array tips.

g) The microneedle array production molds can centri- 15 fuged at 3500 rpm for 3 hours or longer at the required temperature with 0-50 L/min constant purging gas flow through the centrifuge chamber to spin-dry the MNA devices to less than 5% moisture content.

h) The dried microneedle array devices can then be 20 separated from the microneedle array production molds for storage under the desired conditions. In some embodiments, CMC90 based devices can be storable between about 50° C. to -86° C.

Examples of fabricated tip-loaded active cargo carrying 25 microneedle arrays can be seen in FIGS. **3**A-**6**B.

Micromilled Master Molds and Spin-Molded Microneedle Arrays

In the following embodiments, micromilling steps are preformed to create microneedle arrays of various specifi-30 cations. It should be understood, however, that the following embodiments describe certain details of microneedle array fabrication that can be applicable to processes of microneedle array fabrication that do not involve micromilling steps, including the process described above in the 35 previous example.

In the following embodiments, apparatuses and methods are described for fabricating dissolvable microneedle arrays using master molds formed by micromilling techniques. For example, microneedle arrays can be fabricated based on a 40 mastermold (positive) to production mold (negative) to array (positive) methodology. Micromilling technology can be used to generate various micro-scale geometries on virtually any type of material, including metal, polymer, and ceramic parts. Micromilled mastermolds of various shapes and con-45 figurations can be effectively used to generate multiple identical female production molds. The female production molds can then be used to microcast various microneedle arrays.

FIG. 7 illustrates an example of a precision-micromilling 50 system that can be used for fabricating a microneedle mastermold. Mechanical micromilling uses micro-scale (for example, as small as 10 µm) milling tools within precision computer controlled miniature machine-tool platforms. The system can include a microscope to view the surface of the 55 workpiece that is being cut by the micro-tool. The microtool can be rotated at ultra-high speeds (200,000 rpm) to cut the workpiece to create the desired shapes. As noted above, the micromilling process can be used to create complex geometric features with many kinds of material. Various 60 types of tooling can be used in the micromilling process, including, for example, carbide micro-tools. In a preferred embodiment, however, diamond tools can be used to fabricate the microneedle arrays on the master mold. Diamond tooling can be preferable over other types of tooling because 65 it is harder than conventional materials, such as carbide, and can provide cleaner cuts on the surface of the workpiece.

Mastermolds can be micromilled from various materials, including, for example, Cirlex® (DuPont, Kapton® polyimide), which is the mastermold material described in the exemplary embodiment. Mastermolds can be used to fabricate flexible production molds from a suitable material, such as SYLGARD® 184 (Dow Corning), which is the production material described in the exemplary embodiment below. The mastermold is desirably formed of a material that is capable of being reused so that a single mastermold can be repeatedly used to fabricate a large number of production molds. Similarly each production mold is desirably able to fabricate multiple microneedle arrays.

Mastermolds can be created relatively quickly using micromilling technology. For example, a mastermold that comprises a 10 mm×10 mm array with 100 microneedles can take less than a couple of hours and, in some embodiments, less than about 30 minutes to micromill. Thus, a short ramp-up time enables rapid fabrication of different geometries, which permits the rapid development of microneedle arrays and also facilitates the experimentation and study of various microneedle parameters.

The mastermold material preferably is able to be cleanly separated from the production mold material and preferably is able to withstand any heighted curing temperatures that may be necessary to cure the production mold material. For example, in an illustrated embodiment, the silicone-based compound SYLGARD® 184 (Dow Corning) is the production mold material and that material generally requires a curing temperature of about 80-90 degrees Celsius.

Mastermolds can be created in various sizes. For example, in an exemplary embodiment, a mastermold was created on 1.8 mm thick Cirlex® (DuPont, Kapton® polyimide) and 5.0 mm thick acrylic sheets. Each sheet can be flattened first by micromilling tools, and the location where the microneedles are to be created can be raised from the rest of the surface. Micro-tools can be used in conjunction with a numerically controlled micromilling machine (FIG. 1) to create the microneedle features (e.g., as defined by the mastermold). In that manner, the micromilling process can provide full control of the dimensions, sharpness, and spatial distribution of the microneedles.

FIG. 8 is an image from a scanning electron microscope (SEM) showing the structure of a micromilled mastermold with a plurality of pyramidal needles. As shown in FIG. 8, a circular groove can be formed around the microneedle array of the mastermold to produce an annular (for example, circular) wall section in the production mold. The circular wall section of the production mold can facilitate the spincasting processes discussed below. Although the wall sections illustrated in FIG. 9 and the respective mastermold structure shown in FIG. 8 is circular, it should be understood that wall sections or containment means of other geometries can be provided. For example, depending on what shape is desired for the microneedle array device, the containment means can be formed in a variety of shapes including, for example, square, rectangular, trapezoidal, polygonal, or various irregular shapes.

As discussed above, the production molds can be made from SYLGARD® 184 (Dow Corning), which is a two component clear curable silicone elastomer that can be mixed at a 10:1 SYLGARD® to curing agent ratio. The mixture can be degassed for about 10 minutes and poured over the mastermold to form an approximately 8 mm layer, subsequently degassed again for about 30 minutes and cured at 85° C. for 45 minutes. After cooling down to room temperature, the mastermold can be separated from the cured silicone, and the silicone production mold trimmed to the edge of the circular wall section that surrounds the array (FIG. 9.). From a single mastermold, a large number of production molds (e.g., 100 or more) can be produced with very little, if any, apparent deterioration of the Cirlex® or acrylic mastermolds.

FIG. **9** is an SEM image of a pyramidal production mold created as described above. FIG. **10** illustrates an enlarged segment of the production mold with a pyramidal needle molding well in the center of the image. The molding well is configured to receive a base material (and any components 10 added to the base material) to form microneedles with an external shape defined by the molding well.

To construct the microneedle arrays, a base material can be used to form portions of each microneedle that have bioactive components and portions that do not. As discussed 15 above, each microneedle can comprise bioactive components only in the microneedles, or in some embodiments, only in the upper half of the microneedles, or in other embodiments, only in a portion of the microneedle that tapers near the tip. Thus, to control the delivery of the 20 bioactive component(s) and to control the cost of the microneedle arrays, each microneedle preferably has a portion with a bioactive component and a portion without a bioactive component. In the embodiments described herein, the portion without the bioactive component includes the 25 supporting structure of the microneedle array and, in some embodiments, a base portion (e.g., a lower half) of each microneedle in the array.

Various materials can be used as the base material for the microneedle arrays. The structural substrates of biodegradable solid microneedles most commonly include poly(lacticco-glycolic acid) (PLGA) or carboxymethylcellulose (CMC) based formulations; however, other bases can be used.

CMC is generally preferable to PLGA as the base material 35 of the microneedle arrays described herein. The PLGA based devices can limit drug delivery and vaccine applications due to the relatively high temperature (e.g., 135 degrees Celsius or higher) and vacuum required for fabrication. In contrast, a CMC-based matrix can be formed at room temperature in 40 a simple spin-casting and drying process, making CMC-microneedle arrays more desirable for incorporation of sensitive biologics, peptides, proteins, nucleic acids, and other various bioactive components.

CMC-hydrogel can be prepared from low viscosity 45 sodium salt of CMC with or without active components (as described below) in sterile dH2O. In the exemplary embodiment, CMC can be mixed with sterile distilled water (dH_2O) and with the active components to achieve about 25 wt % CMC concentration. The resulting mixture can be stirred to 50 homogeneity and equilibrated at about 4 degrees Celsius for 24 hours. During this period, the CMC and any other components can be hydrated and a hydrogel can be formed. The hydrogel can be degassed in a vacuum for about an hour and centrifuged at about 20,000 g for an hour to remove 55 residual micro-sized air bubbles that might interfere with a spincasting/drying process of the CMC-microneedle arrays. The dry matter content of the hydrogel can be tested by drying a fraction (10 g) of it at 85 degrees Celsius for about 72 hours. The ready-to-use CMC-hydrogel is desirably 60 stored at about 4 degrees Celsius until use.

Active components can be incorporated in a hydrogel of CMC at a relatively high (20-30%) CMC-dry biologics weight ratio before the spin-casting process. Arrays can be spin-cast at room temperature, making the process compat-65 ible with the functional stability of a structurally broad range of bioactive components. Since the master and production

molds can be reusable for a large number of fabrication cycles, the fabrication costs can be greatly reduced. The resulting dehydrated CMC-microneedle arrays are generally stable at room temperature or slightly lower temperatures (such as about 4 degrees Celsius), and preserve the activity of the incorporated biologics, facilitating easy, low cost storage and distribution.

In an exemplary embodiment, the surface of the production molds can be covered with about 50 μ l (for molds with 11 mm diameter) of CMC-hydrogel and spin-casted by centrifugation at 2,500 g for about 5 minutes. After the initial CMC-hydrogel layer, another 50 μ l CMC-hydrogel can be layered over the mold and centrifuged for about 4 hours at 2,500 g. At the end of a drying process, the CMC-microneedle arrays can be separated from the molds, trimmed off from excess material at the edges, collected and stored at about 4 degrees Celsuis. The production molds can be cleaned and reused for further casting of microneedle arrays.

In some embodiments, CMC-solids can be formed with layers that do not contain active components and layers that contain active components. FIGS. **11**A-D illustrate CMC-solids with different shapes (FIGS. **11**A and **11**B) and embedded active cargos on an upper layer which becomes, after micromilling, the portions of the microneedle with the active components. FIG. **11**C illustrates micron sized fluorescent particles layered on a surface of a non-active component containing layer and FIG. **11**D illustrates toluidine blue examples layered on a surface of a non-active component containing layer.

FIGS. **12**A and **12**B also illustrate CMC-solids with different shapes, with FIG. **12**B showing a square shape and FIG. **12**B showing a rectangular shape. Both CMC solids can be milled to dimensions for further processing as described herein. It should be understood that the geometries and the active cargo shown herein are not intended to be limited to the exemplary embodiments.

Example 2

CMC-solids can be prepared with defined geometry and active cargo contents in one or more layers of the prepared structure. Examples of active cargos integrated into CMCsolids are described more detail herein. Upon construction of the CMC-solids with embedded active cargo contained in at least one layer of the CMC-solid, the CMC solids can be milled to project-specific dimensions and micro-milled to fabricate microneedle devices as described herein.

Example 3

In another embodiment, one or more layers of active cargo can be embedded on CMC-solids for direct micromilling of the microneedle array. FIG. **13** illustrates a sample representation of vertical multi-layered deposition and CMC embedding of active cargos on CMC-solids for direct micromilling of MNA devices.

In one exemplary method, microneedle arrays can be fabricated by preparing CMC-solids with a defined geometries and without any active cargo contained therein. Then, blank CMC-solids can be milled to a desired dimension.

As shown in FIG. **13**, active cargo(s) can be deposited onto the CMC-solid in project specific geometric patterns for inclusion of the active cargo(s) specifically in the tips of micro-milled MNA devices.

The methods active cargo deposition onto the CMC-solid blank can include, for example:

1) Direct printing with micro-nozzle aided droplet deposition.

2) Transfer from preprinted matrices.

3) Droplet-deposition with computer controlled robotic systems.

FIG. 14 illustrates layering and spatial distribution of embedded active cargos in a CMC-solid block. After the first layer is deposited (A) it can be covered with a CMC layer (B) that provides the surface for the subsequent deposition of the active cargo (C). The process can be repeated until all 10 desired layers are deposited and encased in a solid CMCblock suitable for the micro-milling process (D-F).

FIG. 15 illustrates a schematic view of a cross-section of a CMC-block encasing the deposits of the active cargo in a spatially controlled manner (A). The method allows 3-di-¹⁵ at 22° C. to fill the needle tips with adenoviral working mensional control and placement of the active components after micro-milling in the MNA-device (B). In panel (B) of FIG. 15, the placement of the active cargos are shown in the stems of the active cargo; however through the control of the milling process the placement can be controlled vertically 20 from the tip to the base of the microneedles. Colors represent different active components or different amount/concentration of the same material.

Thus, a method of vertically layered deposition of active cargos in microneedles is provided by depositing one or 25 more active cargos sequentially on the surface of the CMCsolids in contact with each other or separated by layers of CMC. In some embodiments, horizontal pattern deposition of the active cargos can result in spatial separation of the cargos. By combining vertical and horizontal patterning of 30 active cargo deposition, 3 dimensional delivery and distribution of each of the defined active components can be achieved, further reducing waste of active components during fabrication of microneedle arrays.

Microneedle Integrated Adenovectors

The following embodiments are directed to dissolvable microneedle arrays, such as those described herein, that incorporate infectious viral vectors into the dissolvable matrix of microneedle arrays. Using this technology, for the first time, living viral vectors can be incorporated into 40 microneedle arrays. As described herein, the incorporation of viral vectors within the disclosed microneedle arrays stabilizes the viral vectors so that they maintain their infectivity after incorporation and after prolonged periods of storage. The application of microneedle array incorporated 45 adenovectors (MIAs) to the skin results in transfection of skin cells. In a vaccine setting, we have demonstrated that skin application of MIAs encoding an HIV antigen results in potent HIV specific immune responses. These results are described in detail in the examples below. 50

Example 4

The microneedle integrated adenovectors preparation method described herein preserves the viability of the 55 adenoviral particles during the preparation and in dry storage. These steps were specifically designed based on the physical and chemical properties of CMC microneedle arrays. Viral viability in CMC microneedle arrays was achieved by 60

- Inclusion of low viscosity carboxymethyl cellulose (CMC90) at 2.5% final concentration (step 2.) and by Timed and temperature controlled spin-drying concentra-
- tion of the adenoviral particles in the tips of the microneedle array devices (step 6.). 65
- Controlled partial rehydration of the needle-tip loaded adenoviral particles (step 8.)

Preparation of Tip-Loaded Microneedle Integrated Adenovectors (MIAs):

1) Resuspend adenoviral particles at 2×109 particles/ml density in Trehalose-storage buffer (5% trehalose Sigma-Aldrich USA, 20 mM Tris pH7.8, 75 mM NaCl, 2 mM MgCl2, 0.025% Tween 80)

2) Mix resuspended viral stock with equal volume of 5% CMC90 prepared in Trehasole-storage buffer, resulting in a 1×109 particles/ml density adenoviral working stock.

3) Add adenoviral working stock suspension to the surface of microneedle array production molds (as described in detail in other embodiments herein) at 40 µl per cm2 surface area

4) The molds are centrifuged at 4500 rpm for 10 minutes stock.

5) The excess viral stock is removed and the surface of the molds washed with 100 µl (phosphate buffer saline (PBS) solution per cm2 mold-surface area.

6) The microneedle array-molds containing the adenoviral stock solution only in the needle's cavity are partially spin-dried at 3500 rpm for 10 minutes at 22° C.

7) 100 µl 20% structural, non-cargo containing CMC90 hydrogel in H2O added to the surface microneedle arraymolds' per cm2 mold-area to form the structure of the MIA device.

8) Centrifuge at 4500 rpm for 10 min at 22° C. to fill up the needle cavities with 20% CMC90 and allow 30 min incubation for the rehydration of the adenoviral particles dried in the tips (step 3-6, above).

9) By centrifugation spin-dry the MIA devices to less than 5% moisture content at 3500 rpm for 3 hours at 22° C. with 10 L/min constant air flow through the centrifuge chamber.

10) De-mold the dried MIA devices for storage at 4° C. or 35 -80° C.

Example 5

We have evaluated the potency and stability MNA incorporated recombinant adenoviral particles. Ad5.EGFP was incorporated into CMC hydrogel MNAs to fabricate a final product that contained 1010 virus particles/MNA. Control blank MNAs were prepared identically but without the virus. Batches of Ad5.EGFP and control MNAs were stored at RT, 4° C. and at -86° C. and viral stability was evaluated in infectious assays. Specific transduction activity of the MNA incorporated Ad5.EGFP virus was assessed in vitro using 293T cells. Cells were plated at 2×106/well in six well plates and transduced in duplicate with diluted virus suspension, suspension+empty MNA (control), or Ad5.EGFP MNAs stored at RT, 4° C. and -86° C. for the indicated time periods. As a negative control untransduced wells were included. Initially cell populations were analyzed after 24 h by flow cytometry for GFP expression (representative histogram is shown in FIG. 35.).

As shown in FIG. 35, the incorporation of Ad5.EGFP into MNAs does not reduce transduction efficiency. Flow cytometry analysis of GFP expressing target 293T cells 24 h after transduction with identical titers of Ad5.EGFP either in suspension or incorporated into CMC-patches vs. untransfected control cells. FIG. 36 shows the stability of MNA embedded Ad5.EGFP virus. GFP gene expression was assayed by flow cytometry as in FIG. 37 and normalized to the infection efficiency of -86° C. preserved Ad5.EGFP suspension.

It has been found that the infection efficiency using MNA Ad5.EGFP virus was 87.92±4.5%, which is similar to that observed for traditional -86° C. preserved Ad5.EGFP suspension (FIGS. **35** and **36**), suggesting that the manufacturing process does not adversely affect the transduction efficiency of Ad-EGFP viral particles. To asses infectivity over time, the transfection efficiency of freshly prepared -86° C. 5 preserved Ad5.EGFP suspensions was compared to that of MNA incorporated Ad5.EGFP stored for prolonged periods of time at either RT, 4 C, or -86 C. Infectivity (normalized to Ad5.EGFP suspension+empty CMC-patch) is reported for storage periods of up to 365 days (FIG. **36**). These results 10 suggest that the infectiousness of MNA Ad5.EGFP is remarkably stable with storage at either 4 C or -86 C, and somewhat stable at RT for up to 30 days.

These results demonstrate that microneedle array delivered Ad transgenes are expressed in the skin and induce 15 potent cellular immune responses. To specifically evaluate gene expression in vivo, we determined GFP expression in skin following either traditional intradermal injection (I.D.) or microneedle array-mediated intracutaneous delivery. We delivered 108 Ad5.GFP viral particles by ID injection or 20 topically via a single microneedle array application (FIG. 37). Skin was harvested 48 h later, cryosectioned, counterstained using blue fluorescent DAPI to identify cell nuclei, and then imaged by fluorescent microscopy. Significant cellular GFP expression was observed following both I.D. 25 and microneedle array delivery. To evaluate immunogenicity, we evaluated antigen-specific lytic activity in vivo following a single I.D. or microneedle array immunization without boosting. For this purpose we immunized groups of mice with E1/E3-deleted Ad5-based vectors that encode 30 codon-optimized SIVmac239 gag full-length or SIVmac239 gag p17 antigens (Ad5.SIV gag, Ad5.SIV gag p17). Empty vector was used as a control (Ad5). We observed potent and similar levels of in vivo lytic activity specific for the dominant SIVgag p17-derived peptide KSLYNTVCV (SIV- 35 mac239 gag 76-84) following either I.D. or microneedle array immunization with either Ad5.SIV gag or Ad5.SIV gag p17 (FIG. 37, CTL).

The microneedle array technology disclosed herein can also facilitate clinical gene therapy. It addresses, for 40 example, at least two major limitations of conventional approaches. First, it enables stabilization and storage of recombinant viral vectors for prolonged periods of time. By rendering live virus vectors resistant to high and low temperatures with proven seroequivalence to frozen liquid for-45 mulations, microneedle array stabilization will relieve pressures related to the 'cold chain.' Further, integration in microneedle arrays enables precise, consistent and reproducible dosing of viral vectors not achievable by conventional methods. Finally, the viral vector is repackaged in the 50 only necessary delivery device, the biocompatible and completely disposable microneedle array that directs delivery precisely to the superficial layers of the skin.

Such a gene delivery platform is useful in providing patient-friendly, clinical gene therapy. Since these 55 microneedle arrays have been engineered to not penetrate to the depth of vascular or neural structures, gene delivery to human skin will be both painless and bloodless. In addition, the fabrication process is flexible, enabling simple and rapid low cost production with efficient scale-up potential. Also, 60 as a final product, the MIA device it is stable at room temperature and is inexpensive to transport and store. In combination, these structural and manufacturing advantages can enable broad and rapid clinical deployment, making this gene delivery technology readily applicable to the preven-55 tion and/or treatment of a broad range of human diseases. Moreover, this approach can be extended to other vector-

based vaccine platforms that are currently restricted by the same limitations (e.g., vaccinia virus, AAV etc.). For at least these reasons, the disclosed microneedle arrays and methods of using the same significantly advance the recombinant gene therapy field.

Microneedle Arrays-Exemplary Active Components

Various active components are described in detail below. For convenience, the following examples are based on an microneedle array which is 6.3×6.3 mm. This size, and hence cargo delivery can be varied by increasing or decreasing 2-100 fold.

General considerations for the maximum active cargo quantities include, for example, total needle volume in the array and solubility of the active component(s) in the solvent (generally expected to be <50%).

Tip Loaded Components:	Amount Tip Loaded into MNA device µg/device (unless indicated differently) Live viruses ⁽¹⁾	Max. predicted loading capacity
Ad5.GFP (adeno viral GFP expression vector) Ad-SIVgag (adeno viral gag expression vector) Ad-SIVp17 (adeno viral gag-p17 expression vector) Ψ 5 (non-recombinant Ad vector) Lenti-GFP ⁽²⁾ (Lenti viral GFP expression vector)	$\begin{array}{c} 5\times10^8\\ \text{particles/MNA}\\ 5\times10^8\\ \text{particles/MNA}\\ 5\times10^8\\ \text{particles/MNA}\\ 5\times10^8\\ \text{particles/MNA}\\ 5\times10^6\\ \text{particles/MNA}\end{array}$	2-5 × 10 ⁹ particles/MNA 2-5 × 10 ⁹ particles/MNA 2-5 × 10 ⁹ particles/MNA 2-5 × 10 ⁷ particles/MNA 2-5 × 10 ⁷ particles/MNA

Vaccinia virus (immunization)

Recombinant vaccinia virus (gene therapy, genetic engineering)

Seasonal influenza

MMR (Measles, Mumps, Rubella)

F	Proteins/Peptides	
BSA (FITC labeled)	240	400
OVA (FITC labeled)	100	400
OVA (no label)	240	400
Flu (split vaccine)	0.22	(2-5)
Ej	pitope Peptides ⁽³⁾	(= -)
TRP-2	50	200
EphA2 (a)	50	400
EphA2 (b)	50	400
DLK-1	50	200
Multiple epitopes	200	400-600
in one MNA		
Substance-P	15	
(NK-1R ligand)		
	Nucleic acids	
CpG 1668	120	250
CpG 2006	120	250
Poly(I:C)	250	250
Plasmid vectors	100	200
(High mol. weight DNA)		
Peptide	s/Nucleic acid combos	
OVA/CpG	250/120	
OVA/CpG/polv(I:C)	250/120/250	
Epitope	200/250	
peptides/poly(I:C)		
	Organics	
Doxorubicin	100	
P848 (TIP7/8 ligand)	6	

	. •	
cor	ifin	ned

L733	2	
(NK-1 antagonist)		
DNCB (irritant)	100	
. ,	Particulates	
Micro-particles	1×10^{6}	$2-5 \times 10^{7}$
(1 u diameter	particles/MNA	particles/MNA
microsphares)	1	1

Nano Scale Particles PLG/PLA Based

Other Biolog	gic
tumor lysate/CpG	250/120
tumor lysate/CpG/poly(I:C)	250/120/250
tumor lysates/poly(I:C)	200/250

Tip-loading of live a denoviruses generally includes the $^{\rm 20}$ following modifications:

a) The presence of 5% trehalose and 2.5% CMC90 in the tip-loading hydrogel suspension.

b) The temperature of the process is maintained at 22° C. ²⁵ In addition, Lenti viral vectors generally require 4° C. processing and vapor trap based humidity controls. Also, short epitope peptides generally are solubilized in DMSO, with the evaporation time of the solvent during tip-loading is 4 hours. 30

Microneedle Structures and Shapes

For each of the embodiments below, it should be understood that one or more layers of active components can be provided in the microneedles of the microneedle arrays as described above. Thus, for example, in some embodiments, 35 active components are only provided in the area of the microneedle—not in the structural support of the array, such as shown in FIG. **15**. Moreover, in other embodiments, the active components are concentrated in the upper half of the microneedles, such as in the tips of the microneedles as 40 shown in FIGS. **3A-4**B.

FIGS. **16**A and **16**B are SEM images of a CMC-microneedle array formed with a plurality of pyramidal projections (i.e., microneedles). The average tip diameter of the pyramidal needles shown in FIG. **16**A is about 5-10 μ m. As 45 shown in FIG. **16**B, the sides of the pyramidal needles can be formed with curved and/or arcuate faces that can facilitate insertion in skin.

FIG. **17** is another SEM image of a single needle of a microneedle array. The microneedle shown in FIG. **17** is a 50 base-extended pillar type molded CMC-microneedle. The base-extended pillar type microneedle comprises a base portion, which is generally polyagonal (for example, rectangular) in cross section, and a projecting portion that extends from the base portion. The projecting portion has a 55 lower portion that is substantially rectangular and tip portion that generally tapers to a point. The tip portion is generally pyramidal in shape, and the exposed faces of the pyramid can be either flat or arcuate. The projecting portion can be half or more the entire length of the needle. 60

FIGS. **18** and **19** illustrate micrographs of pyramidal (FIG. **18**) and pillar type (FIG. **19**) molded CMC-microneedles. Because the pyramidal needles have a continually increasing cross-sectional profile (dimension) from the needle point to the needle base, as the needle enters the skin, 65 the force required to continue pushing the pyramidal needle into the skin increases. In contrast, pillar type needles have

a generally continuous cross-sectional profile (dimension) once the generally rectangular portion of the projection portion is reached. Thus, pillar type needles can be preferable over pyramidal type needles because they can allow for the introduction of the needle into the skin with less force.

FIG. 20 illustrates schematic representation of microneedle shapes and structures that are generally suitable for fabrication by spin-casting material into a mastermold formed by micromilling. Since the shapes and structures
10 shown in FIG. 20 do not contain any undercuts, they generally will not interfere with the molding/de-molding process. The structures in FIG. 20 include (a) a generally pyramidal microneedle, (b) a "sharp" pillar type microneedle (without the base member of FIG. 8), (c) a
15 "wide" pillar type microneedle, (d) a "short" pillar type microneedle (having a short pillar section and a longer pointed section), and (e) a "filleted" pillar type microneedle.

While the volume of the pyramidal microneedles can be greater than that of the pillar type microneedles, their increasing cross-sectional profile (dimension) requires an increasing insertion force. Accordingly, the geometry of the pyramidal microneedles can result in reduced insertion depths and a reduced effective delivery volume. On the other hand, the smaller cross-sectional area and larger aspect ratio of the pillar microneedles may cause the failure force limit to be lower. The smaller the apex angle α , the "sharper" the tip of the microneedle. However, by making the apex angle too small (e.g., below about 30 degrees), the resulting microneedle volume and mechanical strength may be reduced to an undesirable level.

The penetration force of a microneedle is inversely proportional to the microneedle sharpness, which is characterized not only by the included (apex) angle of the microneedles, but also by the radius of the microneedle tip. While the apex angle is prescribed by the mastermold geometry, the tip sharpness also depends on the reliability of the mold. Micromilling of mastermolds as described herein allows for increased accuracy in mold geometry which, in turn, results in an increased accuracy and reliability in the resulting production mold and the microneedle array formed by the production mold.

The increased accuracy of micromilling permits more accurate and detailed elements to be included in the mold design. For example, as discussed in the next section below, the formation of a fillet at the base of a pillar type microneedle can significantly increase the structural integrity of the microneedle, which reduces the likelihood that the microneedle will fail or break when it impacts the skin. While these fillets can significantly increase the strength of the microneedles, they do not interfere with the functional requirements of the microneedles (e.g., penetration depth and biologics volume). Such fillets are very small features that can be difficult to create in a master mold formed by conventional techniques. However, the micromilling techniques described above permit the inclusion of such small features with little or no difficulty.

Mechanical Integrity and Penetration Capabilities

Microneedle arrays are preferably configured to penetrate the stratum corneum to deliver their cargo (e.g., biologics or bioactive components) to the epidermis and/or dermis, while minimizing pain and bleeding by preventing penetration to deeper layers that may contain nerve endings and vessels. To assess the mechanical viability of the fabricated microneedle arrays, tests were performed on the pyramidal and pillar type microneedle arrays as representative variants of array geometry (shown, e.g., in FIGS. **7**B and **8**). The first set of tests illustrate the failure limit of microneedles, and include pressing the microneedle array against a solid acrylic surface with a constant approach speed, while simultaneously measuring the force and the displacement until failure occurs. The second set of tests illustrate the piercing capability of the microneedles on human skin explants.

FIG. 21 illustrates a test apparatus designed for functional testing. The sample (i.e., microneedle array) was attached to a fixture, which was advanced toward a stationary acrylic artifact (PMMA surface) at a constant speed of about 10 mm/s speed using a computer-controlled motion stage (ES14283-52 Aerotech, Inc.). A tri-axial dynamometer (9256C1, Kistler, Inc.) that hosted the acrylic artifact enabled high-sensitivity measurement of the forces.

FIG. 22 illustrates force-displacement curves of data 15 measured during failure tests. The curve on the left is representative of data obtained from testing a pillar microneedle sample and the curve on the right is representative of data obtained from testing a pyramid microneedle. As seen in FIG. 22, the failure of these two kinds of 20 microneedles are significantly different; while the pyramidal arrays plastically deform (bend), the pillar type arrays exhibit breakage of the pillars at their base. This different failure behavior lends itself to considerably different displacement-force data. The failure (breakage) event can be 25 easily identified from the displacement-force data as indicated in the figure. Based on the obtained data, the failure point of pillar type microneedles was seen to be 100 mN in average. As only about 40 mN of force is required for penetration through the stratum corneum, the microneedles 30 are strong enough to penetrate human skin without failure. Furthermore, since parallelism between microneedle tips and the acrylic artifact cannot be established perfectly, the actual failure limit will likely be significantly higher than 100 mN (i.e., microneedles broke in a successive manner, 35 rather than simultaneous breakage of most/all microneedles).

The pyramidal microneedles presented a continuously increasing force signature with no clear indication of point of failure. To identify the failure limit for the pyramidal 40 microneedles, interrupted tests were conducted in which the microneedles were advanced into the artifact by a certain amount, and retreated and examined through optical microscope images. This process was continued until failure was observed. For this purpose, the failure was defined as the 45 bending of the pyramidal microneedles beyond 15 degrees.

To further analyze the failure of the microneedles, the finite-elements model (FEM) of the microneedle arrays shown in FIG. 23 was developed. To obtain the mechanical properties (elastic modulus and strength limit) of the CMC 50 material, a series of nanoindentation tests (using a Hysitron nanoindentor). The average elastic modulus and yield strength of the CMC material (as prepared) were 10.8 GPa and 173 MPa, respectively. This indicates that the prepared CMC material has a higher elastic modulus and yield 55 strength than both PMMA (elastic modulus: 3.1 GPa, yield strength: 103 MPa) and polycarbonate (elastic modulus: 2.2 GPa, yield strength: 75 MPa), indicating the superior strength and stiffness of CMC material with respect to other polymers.

Using this data, a series of FEM simulations were conducted. It was predicted from the FEM models that failure limit of pyramidal and sharp-pillar (width=134 µm) microneedles with 600 µm height, 30 degree apex angle, and 20 um fillet radius were 400 mN (pyramid) and 290 mN 65 (sharp-pillar) for asymmetric loading (5 degrees loading misorientation). Considering that the minimum piercing

force requirement is about 40 mN, pyramid and sharp-pillar microneedles would have factors of safety of about 10 and 7.25, respectively.

When the fillet radius is doubled to 40 µm, the failure load for the pillar was increased to 350 mN, and when the fillet radius is reduced to 5 µm, the failure load was reduced to 160 mN, which is close to the experimentally determined failure load. The height and width of the pillars had a significant effect on failure load. For instance, for 100 µm width pillars, increasing the height from 500 µm to 1000 µm reduced the failure load from 230 mN to 150 mN. When the width is reduced to 75 µm, for a 750 µm high pillar, the failure load was seen to be 87 mN.

To evaluate penetration capability, pyramidal and sharppillar microneedle arrays were tested for piercing on waterbased model elastic substrates and on full thickness human skin. FIG. 24 illustrates stereo micrographs of pyramidal (Panels A, C, and E) and pillar type microneedle arrays (B, D, and F) after 4 minutes of exposure to model elastics. In particular, toluene blue tracer dye was deposited in model elastic substrates (Panels C and D) or freshly excised full thickness human skin explants (Panels E and F) after application of pyramidal or pillar type microneedle arrays.

The model elastic substrate comprised about 10% CMC and about 10% porcine gelatin in PBS gelled at about 4 degrees Celsius for about 24 hours or longer. The surface of the elastics was covered with about 100 µm thick parafilm to prevent the immediate contact of the needle-tips and the patch materials with the water based model elastics. To enable stereo microscopic-imaging, trypan blue tracer dye (Sigma Chem., cat #T6146) was incorporated into the CMChydrogel at 0.1% concentration. The patches were applied using a spring-loaded applicator and analyzed after about a 4 minute exposure. Based on physical observation of the dye in the target substrates, the dissolution of the microneedles of the two different geometries was markedly different.

The sharp-pillar needles applied to the model elastic substrate released substantially more tracer dye to the gel matrix than that observed for the pyramidal design (FIG. 24, C vs. D). Images of the recovered patches (FIG. 24, A vs. B) were consistent with this observation, as the degradation of the sharp-pillar needles was more advanced than that of the pyramidal needles. To extrapolate this analysis to a more clinically relevant model, pyramidal and pillar type microneedle arrays were applied to freshly excised full thickness human skin explants using the same force from the spring loaded applicator. Consistent with results from the elastic model, the pyramidal microneedle arrays deposited visibly less tracer dye than the sharp-pillar microneedle arrays (FIG. 24, E vs. F).

To further evaluate penetration and to assess delivery effectiveness to human skin, CMC-microneedle arrays were fabricated with BioMag (Polysciences, Inc., cat#. 84100) beads or fluorescent particulate tracers (Fluoresbrite YG 1 µm, Polysciences Inc., cat#. 15702). The pyramidal CMCmicroneedle arrays containing fluorescent or solid particulates were applied to living human skin explants as described previously. Five minutes after the application, surface residues were removed and skin samples were 60 cryo-sectioned and then counterstained with toluene blue for imaging by light microscopy (FIGS. 25A and 25B) or by fluorescent microscopy (FIG. 25C).

Pyramidal CMC-microneedles effectively penetrated the stratum corneum, epidermis, and dermis of living human skin explants, as evidenced by the deposition of Biomag beads lining penetration cavities corresponding to individual needle insertion points (representative sections shown in

FIGS. **25**A and **25**B). In particular, ordered cavities (FIG. **25**A, cavities numbered 1-4, toluene blue counterstain, 10×) and deposits of BioMag particles (brown) lining penetration cavities were evident (FIG. **25**B, 40×), indicating microneedle penetrated of human skin. Further, analysis of sections from living human explants stained with DAPI to identify cell nuclei and anti-HLA-DR to identify MHC class II+ antigen presenting cells revealed high density fluorescent particulates deposited in the superficial epidermis and dermis, including several particles co-localized with class II+ antigen presenting cells (FIG. **25**C, DAPI (blue), HLA-DR+ (red) and fluorescent particles (green), 40×).

These results further demonstrate that the CMC microneedle arrays described herein can effectively penetrate human skin and deliver integral cargo (bioactive components), including insoluble particulates. They are consistent with effective delivery of particulate antigens to antigen presenting cells in human skin, currently a major goal of rational vaccine design.

To further address microneedle array delivery in vivo, the cutaneous delivery of particulate antigen in vivo was modeled by similarly applying fluorescent particle containing content of the excised human skin explants-discs was determined by scintillation counting. The specific activity of the 3H-CMC-microneedle patch-material was determined and calculated to be 72,372 cpm/mg dry weight. This specific activity was used to indirectly determine the amount of ovalbumin delivered to and retained in the skin. The resulting data is summarized in Table 1 below.

The tested types of patches were consistent from microneedle array to microneedle array (average standard deviation 24-35%) and batch to batch (average standard deviation 7-19%). The intra-batch variability for both needle geometry was lower than the in-batch value indicating that the insertion process and the characteristics of the target likely plays a primary role in the successful transdermal material delivery and retention. The patch-material retention data clearly demonstrate the foremost importance of the microneedle geometry in transdermal cargo delivery. Pillartype needle geometry afforded an overall 3.89 fold greater deposition of the 3H labeled needle material than that of the pyramidal needles. On the basis of the deposited radioactive material, it is estimated that the pyramidal needles were inserted about 200 µm deep while the pillar-type were inserted about 400 µm or more.

TABLE 4.2.5

Transfer of ³ H-labeled CMC-microneedle material into human skin explants by pyramidal and pillar-type needles.									
Array Batches	Pyramid Needles (cpm/patch)	STDev (%)	Pyramidal Needles OVA Transferred (µg/patch)	Pillar-Type Needles (cpm/patch)	STDev (%)	Pillar-Type Needles OVA Transferred (µg/patch)	Pillar to Pyramid Ratio		
Batch A	2459.00	17.56	1.70	11700.50	31.52	8.08	4.76		
Batch B	3273.50	57.39	2.26	12816.50	21.45	8.85	3.92		
Batch C	2757.75	46.13	1.90	12240.00	26.77	8.46	4.44		
Batch D	3782.00	36.27	2.61	10921.50	9.32	7.55	2.89		
IntraBatch AVG	3068.06	19.00	2.12	11919.63	6.77	8.24	3.89		

arrays to the dorsal aspect of the ears of anesthetized mice. After 5 minutes, patches were removed and mice resumed their normal activity. Three hours or 3 days, ear skin and draining lymph nodes were analyzed for the presence of fluorescent particles. Consistent with observations of human skin, particulates were evident in the skin excised from the array application site (data not shown). Further, at the 3 day time point, substantial numbers of particles were evident in the draining lymph nodes. FIGS. **26A** and **26B** illustrates substantial numbers of particles that were evident in the draining lymph Nodes (FIG. **26A**, 10×), including clusters of particulates closely associated with Class II+ cells (FIG. 50 **26**B, 60×) suggesting the presence of lymph node resident antigen presenting cells with internalized particulates.

To quantitatively evaluate the effects of needle geometry on cargo delivery using microneedle arrays, 3H-tracer labeled CMC-microneedle arrays were constructed. The 55 CMC-hydrogel was prepared with 5% wt ovalbumin as a model active component at 25 wt % final dry weight content (5 g/95 g OVA/CMC) and trace labeled with 0.1 wt % trypan blue and 0.5×106 dpm/mg dry weight 3H-tracer in the form of 3H-thymidine (ICN Inc., cat #2406005). From a single 60 batch of labeled CMC-hydrogel-preparation four batches of 3H-CMC-microneedle arrays were fabricated, containing several individual patches of pyramidal and sharp-pillar needle geometry. The patches were applied to human skin explants as described above and removed after 30 min 65 exposure. The patch-treated area was tape-striped to remove surface debris and cut using a 10 mm biopsy punch. The 3H

Desirably, the microneedle arrays described herein can be used for cutaneous immunization. The development of strategies for effective delivery of antigens and adjuvants is a major goal of vaccine design, and immunization strategies targeting cutaneous dendritic cells have various advantages over traditional vaccines.

The microneedle arrays described herein can also be effective in chemotherapy and immunochemotherapy applications. Effective and specific delivery of chemotherapeutic agents to tumors, including skin tumors is a major goal of modern tumor therapy. However, systemic delivery of chemotherapeutic agents is limited by multiple well-established toxicities. In the case of cutaneous tumors, including skin derived tumors (such as basal cell, squamous cell, Merkel cell, and melanomas) and tumors metastatic to skin (such as breast cancer, melanoma), topical delivery can be effective. Current methods of topical delivery generally require the application of creams or repeated local injections. The effectiveness of these approaches is currently limited by limited penetration of active agents into the skin, nonspecificity, and unwanted side effects.

The microneedle arrays of the present disclosure can be used as an alternative to or in addition to traditional topical chemotherapy approaches. The microneedle arrays of the present disclosure can penetrate the outer layers of the skin and effectively deliver the active biologic to living cells in the dermis and epidermis. Delivery of a chemotherapeutic agents results in the apoptosis and death of skin cells.

Further, multiple bioactive agents can be delivered in a single microneedle array (patch). This enables an immuno-

chemotherapeutic approach based on the co-delivery of a cytotoxic agent with and immune stimulant (adjuvants). In an immunogenic environment created by the adjuvant, tumor antigens releases from dying tumor cells will be presented to the immune system, inducing a local and 5 systemic anti-tumor immune response capable of rejecting tumor cells at the site of the treatment and throughout the body.

In an exemplary embodiment, the delivery of a biologically active small molecule was studied. In particular, the 10 activity of the chemotherapeutic agent Cytoxan® delivered to the skin with CMC microneedle arrays was studied. The use of Cytoxan® enables direct measurement of biologic activity (Cytoxan® induced apoptosis in the skin) with a representative of a class of agents with potential clinical 15 utility for the localized treatment of a range of cutaneous malignancies.

To directly evaluate the immunogenicity of CMC microneedle array incorporated antigens, the well characterized model antigen ovalbumin was used. Pyramidal 20 arrays were fabricated incorporating either soluble ovalbumin (sOVA), particulate ovalbumin (pOVA), or arrays containing both pOVA along with CpGs. The adjuvant effects of CpGs are well characterized in animal models, and their adjuvanticity in humans is currently being evaluated in 25 need for molding steps and enables a simplified, scalable, clinical trials.

Immunization was achieved by applying antigen containing CMC-microneedle arrays to the ears of anesthetized mice using a spring-loaded applicator as described above, followed by removal of the arrays 5 minutes after applica- 30 tion. These pyramidal microneedle arrays contained about 5 wt % OVA in CMC and about 0.075 wt % (20 µM) CpG. As a positive control, gene gun based genetic immunization strategy using plasmid DNA encoding OVA was used. Gene gun immunization is among the most potent and reproduc- 35 ible methods for the induction of CTL mediated immune responses in murine models, suggesting its use as a "gold standard" for comparison in these assays.

Mice were immunized, boosted one week later, and then assayed for OVA-specific CTL activity in vivo. Notably, 40 immunization with arrays containing small quantities of OVA and CpG induced high levels of CTL activity, similar to those observed by gene gun immunization (FIG. 27). Significant OVA-specific CTL activity was elicited even in the absence of adjuvant, both with particulate and soluble 45 array delivered OVA antigen. It is well established that similar responses require substantially higher doses of antigen when delivered by traditional needle injection.

To evaluate the stability of fabricated arrays, batches of arrays were fabricated, stored, and then used over an 50 extended period of time. As shown in FIG. 28, no significant deterioration of immunogenicity was observed over storage periods spanning up to 80 days (longest time point evaluated). Thus, the CMC microneedle arrays and this delivery technology can enable effective cutaneous delivery of anti-55 gen and adjuvants to elicit antigen specific immunity.

To evaluate the delivery of a biologically active small molecule, pyramidal CMC-microneedle arrays were fabricated with the low molecular weight chemotherapeutic agent Cytoxan® (cyclophosphamide), or with FluoresBrite green 60 fluorescent particles as a control. Cytoxan® was integrated at a concentration of 5 mg/g of CMC, enabling delivery of approximately about 140 µg per array. This is a therapeutically relevant concentration based on the area of skin targeted, yet well below levels associated with systemic 65 toxicities. Living human skin organ cultures were used to assess the cytotoxicty of Cytoxan®. Cytoxan® was deliv-

ered by application of arrays to skin explants as we previously described. Arrays and residual material were removed 5 minutes after application, and after 72 hours of exposure, culture living skin explants were cryo-sectioned and fixed. Apoptosis was evaluated using green fluorescent TUNEL assay (In Situ Cell Death Detection Kit, TMR Green, Roche, cat#:11-684-795-910). Fluorescent microscopic image analysis of the human skin sections revealed extensive apoptosis of epidermal cells in Cytoxan® treated skin as shown in FIG. 29A. As shown in FIG. 29B, no visible apoptosis was observed in fluorescent particle treated skin though these particles were evident, validating that the observed area was accurately targeted by the microneedle array.

Direct Fabricated Microneedle Arrays

The micromilling of mastermolds described above allows the production of microneedle arrays with a variety of geometries. In another embodiment, systems and methods are provided for fabricating a microneedle array by directly micromilling various materials, such as dried CMC sheets. The same general tooling that was described above with respect to the micromilling of mastermolds can be used to directly micromilling microneedle arrays.

Direct micromilling of microneedle arrays eliminates the and precisely reproducible production strategy that will be compatible with large scale clinical use. Moreover, direct fabrication of the microneedle arrays through micromilling enables greater control of microneedle geometries. For example, micromilling permits the inclusion of microneedle retaining features such as undercuts and/or bevels, which cannot be achieved using molding processes.

The reproducibility of direct milling of microneedle arrays is particular beneficial. That is, in direct micromilling all of the microneedles are identical as a result of the milling fabrication process. In molding operations, it is not uncommon for some needles to be missing or broken from a given patch as a result of the process of physically separating them from the molds. For use in certain medical applications, the reproducibility of the amount of bioactive components in the array is very important to provide an appropriate level of "quality control" over the process, since irregularities in the needles from patch to patch would likely result in variability in the dose of drug/vaccine delivered. Of course, reproducibility will also be an important benefit to any application that requires FDA approval. Spincast/molded patches would require special processes to assure acceptable uniformity for consistent drug delivery. This quality control would also be likely to result in a certain percentage of the patches "failing" this release test, introducing waste into the production process. Direct micromilling eliminates or at least significantly reduces these potential problems.

Molding processes also have inherent limitations because of the need to be able to fill a well or concavity and remove the cured molded part from that well or concavity. That is because of mold geometries, undercuts must generally be avoided when molding parts or the part will not be removable from the mold. That is, a geometrical limitation of a molded part, such as a molded microneedle array, is that any feature located closer to the apex must be narrower than any feature located toward the base.

Accordingly, in view of these limitations, FIG. 20 illustrates schematic representation of microneedle shapes and structures that are generally suitable for fabrication by molding. That is, the shapes and structures shown in FIG. 20 do not contain any undercuts that would prevent the part (i.e., the microneedles) from being removed from a production mold. In contrast, FIG. **30** illustrates a beveled, undercut microneedle shape that cannot be molded in the manners described herein.

This geometry can only be created through direct fabrication using the proposed micromilling technology. The 5 negative (bevel) angle facilitates better retention of the microneedles in the tissue. In addition, because the microneedle of FIG. 30 has a wider intermediate portion (with a larger cross-sectional dimension) above a lower portion (with a smaller cross-sectional dimension), a greater amount of the bioactive material can be delivered by configuring the microneedle to hold or store the bioactive material in the wider section, which is configured to be retained within the skin. Thus, the larger cross-sectional dimension of the intermediate portion can "carry" the bulk 15 of the bioactive component. Since the lower portion tapers to a narrower cross-sectional dimension, the wider intermediate portion will obtain good penetration for delivery of the bioactive component into the skin layer. A portion above the intermediate portion desirably narrows to a point to facilitate 20 entry of the microneedles into the skin layers.

Also, by using a lamination structure to form a sheet or block that can be micromilled, various active components can be integrated into a single microneedle by vertical layering. For example, in an exemplary embodiment, CMC- 40 hydrogel and CMC-sOVA-hydrogel (80% CMC/20 wt % OVA) were layered into the form of a sheet or block. This composite sheet can be micro-machined using the direct micromilling techniques described herein.

FIG. **31** is a stereo-microscopic image analysis of an 45 entire microneedle array. The microneedle comprises a 10×10 array of microneedles. FIG. **32** is an enlarged segment of the microneedle array of FIG. **31**. The layering of two components is shown in FIG. **32**, which illustrates darker areas of the microneedles at tip portions and lighter 50 areas of the microneedles at base portions. The darker layer at the tip represents the layer comprising a bioactive component, in this case soluble ovalbumin contained in a CMC layer.

Although the formation of a layer containing active 55 material (e.g., antigen) and the subsequent micromilling of the layer (and any other adjacent layers) may require the use of relatively large amounts of the active material, the material can be removed (e.g., in the form of chips), recovered, and recycled. Direct machining technology is not restricted 60 by the geometrical constraints arising from the molding/demolding approach, and thus, is capable of creating more innovative needle designs (e.g., FIG. **30**), which can significantly improve the retained needle-volume and needle retention time in the skin.

The production of sheets or blocks by forming a plurality of layers can provide a solid material that can be micromachined and which can comprise one or more layers with a bioactive component. For example, a dissoluble solid carboxymethylcellulose polymer based block or sheet with well-defined and controlled dimensions can be fabricated by a lamination process. The resulting sheet or block can be fully machineable, similar to the machining of plastic or metal sheets or blocks. As described herein, the fabrication process can be suitable for the incorporation of bioactive components into the matrix without significantly reducing their activity levels.

As described below, a fabricated sheet of material (such as a CMC based material) can be directly micro-machined/ micromilled) to produce one or more microneedle arrays suitable for delivering active ingredients through the skin. This dissoluble biocompatible CMC block-material can be used for the delivery of soluble or insoluble and particulate agents in a time release manner for body surface application. The biocompatible material can be suitable for implants in deeper soft or hard tissue when dissolution of the scaffolding material is required and useful.

The following method can be used to prepare a carboxymethylcellulose (CMC) polymer low viscosity hydrogel to 12.5% concentration. The 12.5% carboxymethylcellulose (CMC) low viscosity hydrogel can be prepared in water or other biocompatible buffer, such as (but not limited to) PBS or HBS. During the preparation of the polymer solution, soluble agents (such as nucleic acid, peptides, proteins, lipids or other organic and inorganic biologically active components) and particulates can be added (e.g. ovalbumin, a soluble agent). Ferrous particulates carrying active ingredients at 20 w/w % of CMC can be used.

The preparation of 1000 g sterile 12.5% CMC hydrogel with no active component can be achieved as follows:

1) Measure 125 g CMC, add 875 g water or other water based solvent.

2) Stir to homogeneity in overhead mixer.

3) Autoclave homogenate to sterility at 121 degrees Celsius for 1 hour (the autoclaving step can reduce viscosity for improved layering)

4) Cool to 22 degrees Celsius.

5) Vacuum treat the resulting material at 10 torr and 22 degrees Celsius for 1 hour to remove trapped micro-bubbles.

6) Centrifuge product at 25,000 g for 1 hour in vacuum chambered centrifuge (for floating and further removing residual micro bubbles).

7) Store the CMC-hydrogel product at 4 degrees Celsius.

The preparation of 1000 g sterile 12.5 w/w % dry content 20/80% ovalbumin/CMC hydrogel can be achieved as follows:

1) Measure 100 g CMC add 650 g water or other water based solvent.

2) Stir to homogeneity in overhead mixer.

3) Autoclave homogenate to sterility at 121 degrees Celsius for 1 hour (this autoclaving step can reduce viscosity for improved layering).

4) Cool to 22 degrees Celsius.

5a) Dissolve 25 g ovalbumin in 225 g water.

5b) Sterile filter ovalbumin solution on 0.22 μ m pore sized filter.

6) Mix to homogeneity, under sterile conditions the 750 g CMC hydrogel with 250 g sterile ovalbumin solution.

7) Vacuum treat the resulting material at 10 torr and 22 degrees Celsius for 1 hour to remove trapped micro-bubbles.

8) Centrifuge product at 25,000 g for 1 hour in vacuum chambered centrifuge (for floating and further removing residual micro bubbles).

9) Store the CMC-hydrogel product at 4 degrees Celsius.

10

25

The preparation of 100 g sterile 12.5 w/w % dry content 20/80% particulate-ovalbumin/CMC hydrogel can be achieved as follows:

1) Measure 10 g CMC add 87.5 g water or other water based solvent.

2) Stir to homogeneity in overhead mixer.

3) Autoclave homogenate to sterility at 121 degrees Celsius for 1 hour (this autoclaving step can reduce viscosity for improved layering).

4) Cool to 22 degrees Celsius.

5) Disperse 2.5 g particulate-ovalbumin in the 97.5 g, 22 degrees Celsius CMC-hydrogel and mix to homogeneity, under sterile conditions.

6) Vacuum treat the resulting material at 10 torr and 22 $_{15}$ degrees Celsius for 2 hour to remove trapped micro-bubbles.

7) Centrifuge product at 3,000 g for 1 hour in vacuum chambered centrifuge (for floating and further removing residual micro bubbles).

8) Store the CMC-hydrogel product at 4 degrees Celsius. 20

Note in this example, particulate-ovalbumin is prepared from activated iron beads reaction to ovalbumin. However, it should be noted that the above descriptions are only exemplary embodiments and other compounds and active ingredients can be used.

A solid block/sheet carboxymethylcellulose (CMC) can be fabricated in the following manner using the low viscosity CMC-hydrogels described above.

The fabrication process can comprise a laminar spreading of the polymer at a defined thickness and a drying of the 30 layered polymer to less than about 5% water content using sterile dried air flow over the surface of the polymer layer. The above two acts can repeated until the desired block thickness is achieved.

A method of performing a laminar CMC-hydrogel layer- 35 ing of a defined thickness over the casting mold assembly is described with reference to FIG. 33. FIG. 33 illustrates a cross-sectional view of the casting-mold assembly which includes: (a) casting bed; (b) adjustable casting bed wall; (c) casting-bed depth adjustment assembly; and (d) an acrylic 40 spreader. It should be noted that FIG. 33 is not drawn to scale or otherwise shown with elements in their proper proportions.

The casting mold assembly can be constructed from acrylic (Plexiglas) and can comprise a casting bed base unit, 45 a vertically adjustable hydrophobic casting-bed wall, and a casting-bed adjustment mechanism. The casting bed base unit (a1) can include a removable/replaceable casting bed top plate (a2) with an attached cellulose layer (a3). The cellulose layer can be about 0.5 mm in thickness. The 50 vertically adjustable hydrophobic casting-bed wall (b) can be adjusted using the casting-bed depth adjustment mechanism, which can be comprised of lead-screw (c1) and level adjustment knob (c2). In the illustrated embodiment, a quarter turn of this knob can result in a 0.5 mm lift of the bed 55 wall.

Initially, the adjustable casting bed wall can be set to height where the distance between the acrylic spreader and the cellulose layer of the bed is about 1 mm when the spreader is in position. A predefined volume (e.g., about 0.1 60 ml/cm2) of the 12.5% CMC-hydrogel can be added and layered. The layer can be evened or leveled by sliding the acrylic spreader (d) on the top surface of the adjustable casting wall to yield an even layer of about 1 mm of CMC-hydrogel. The layered CMC-hydrogel can be dried to 65 a solid phase in the drying apparatus shown in FIG. 34 and described in more detail below.

The layering and drying steps can be repeated until the desired layered structure (sheet) is achieved. The casting bed wall can be raised by an appropriate amount during the addition of each layer. For example, after adding each layer, the bed wall can be raised or lifted by about 0.5 mm. Thus, the above-described cycle can deposit about 0.5 mm solid CMC layer. The process (e.g., the layering of material, the raising of bed wall, etc.) can be repeated until the desired block thickness achieved.

The layered CMC-hydrogel polymer can be dried in various manners. For example, FIG. 34 illustrates a drying apparatus that can be used to dry the various deposited layers of the sheet material. It should be noted that FIG. 34 is not drawn to scale or otherwise shown with elements in their proper proportions. A fan can provide continuous gas flow (e.g., air or other inert gas, such as nitrogen) over the CMC-hydrogel layered in the casting mold assembly. The gas flow will result in a gentle dehydration of the CMChydrogel layer. The drying speed can be adjusted to prevent or reduce gas enclosures (e.g., air bubbles) in the solid CMC product. The humid air over the layer can be dried over desiccant (e.g., an air dryer or dehumidifier), temperature adjusted, and returned over the hydrogel again by the speed-controlled fan. A hygrometer can be positioned on the humid side of the chamber to provide an indication of the status of the drying process. After a predetermined dryness has been achieved, as indicated by the hygrometer, the drying process can be ended.

Airflow can be adjusted to affect the drying speed. In the exemplary embodiment, the airflow is controlled to be between about 0.1-2.0 m/sec; the temperature is between ambient and about 50 degrees Celsius. Using these configurations, the drying time of a single layer CMC-hydrogel can be about 0.5-4 hours depend on the airflow and the set temperature.

The pure CMC based product can be transparent, light off white, or amber colored. Its specific gravity can be about 1.55-1.58 g/ml. The product is desirably free of microbubbles and otherwise suitable for fabricating micron scale objects. The physical characterization of the final block/ sheet product (hardness, tensile strength, etc.) can vary, but should generally be able to resist physical stresses associated with micromilling.

As described above, the microneedle arrays disclosed herein are capable of providing reliable and accurate delivery methods for various bioactive components. The structural, manufacturing, and distribution advantages characteristic of the above-described microneedle arrays can be particularly applicable for use in delivering vaccines. Advantages of these microneedle arrays include (1) safety, obviating the use of needles or living vectors for vaccine delivery, (2) economy, due to inexpensive production, product stability, and ease of distribution, and 3) diversity, via a delivery platform compatible with diverse antigen and adjuvant formulations.

Moreover, cutaneous immunization by microneedle array has important advantages in immunogenicity. The skin is rich in readily accessible dendritic cells (DCs), and has long been regarded as a highly immunogenic target for vaccine delivery. These dendritic cell populations constitute the most powerful antigen presenting cells (APCs) identified thus far. For example, genetic immunization of skin results in transfection and activation of dendritic cells in murine and human skin, and these transfected dendritic cells synthesize transgenic antigens, migrate to skin draining lymph nodes, and efficiently present them through the MHC class I restricted pathway to stimulate CD8+ T-cells. The immune responses

induced by skin derived DCs are remarkably potent and long-lasting compared to those induced by other immunization approaches. Recent clinical studies demonstrate that even conventional vaccines are significantly more potent when delivered intradermally, rather than by standard intramuscular needle injection. Thus, microneedle arrays can efficiently and simultaneously deliver both antigens and adjuvants, enabling both the targeting of DCs and adjuvant engineering of the immune response using the same delivery platform.

High Frequency Electro-magnetic Oscillating Applicator Microneedle array devices can be applied to human skin by a variety of methods including self or assisted application by human pressure (e.g., pushing with a finger or thumb), or with spring-loaded devices. To facilitate the ease and repro-15 ducibility of delivery of microneedle array devices, including tip-loaded microneedle arrays, an applicator device is described herein. The applicator device is configured to convert high frequency electromagnetic oscillation into unidirectional mechanical resonance of the active head. This in 20 turn enables multiple reproducible low amplitude and high frequency pressure strokes that facilitate insertion of the microneedles of microneedle arrays into tissues including human skin.

As shown in FIG. **38**, the applicator can comprise an 25 applicator head, an oscillator-energy converter, an electromagnetic oscillator, and a power source. If desired, one, or all of these four elements can be detachable from the applicator device.

An applicator head can be interchangeable to accommo- 30 date and act on different sized and shaped tissue surface areas. As shown in FIG. **39**, various applicator head geometries can be utilized in combination with the applicator described herein. Applicator heads are interchangeable made of stainless steel or other chemically and physically resistant 35 materials. If desired, the applicator heads can be autoclaved for sterility and/or sterilized by alcohols or other chemicals. Alternatively, or in addition, gas sterilization (ethylene oxide) is possible.

Application specific geometries can be rapidly designed 40 and fabricated. For example, the area of a single application in this example can range from 5 mm² to 250 mm² dependent on the active head's geometry. A broader range can be achieved by simple structural variation of the head's geometry. 45

The oscillator energy converter unit can be configured to transforms the electro-magnetic oscillation into mechanical movements of the applicator head. The amplitude of the applicator head's in direction Z can be controlled between 0.5-2.5 mm (FIG. 40; A). In some embodiments, head 50 movements in direction X-Y can be configured to be negligible, <0.2 mm (FIG. 40; B). The frequency of the mechanical movements resulting from the energy conversion in the direction Z can be controlled between 500-25000 rpm. If desired, the oscillator energy converter unit can be 55 detachable and can be disposed or sterilized as needed.

The electro-magnetic (EM) oscillator can be composed of three subunits. These subunits can include a (1) regulated power supply generating the voltage and power for the controller and high frequency EM oscillator; a (2) controller-regulator generates the high frequency signal and the required current for the EM oscillator; and (3) an EM oscillator. The output frequency can be controlled by the user (e.g., in ranges such as from 100-500 Hz). In some embodiments, the EM oscillator can be fully enclosed and 65 can be sterilized by alcohol solutions or other chemical agents.

The power source unit can also be detachable to accommodate different attachable power sources such as:

a. Battery, regular disposable alkaline or any other type. b. Rechargeable NiCad or Li oxide battery with built in inductive charger.

c. Electronic power adapter to 100-240 V

The applicator can provide several benefits in connection with microneedle array application. For example, the applicator can minimalize the mechanical force needed for microneedle array insertion into tissues. The applicator can also reduce pain effects compared to existing spring-loaded applicators. In addition, the applicator can be portable and the components of the applicator can be detachable and interchangeable. Finally, the applicator can be configured so that it is capable of being sterilized for aseptic use.

In view of the many possible embodiments to which the principles of the disclosed embodiments may be applied, it should be recognized that the illustrated embodiments are only preferred examples and should not be taken as limiting the scope of protection. Rather, the scope of the protection is defined by the following claims. We therefore claim all that comes within the scope and spirit of these claims.

We claim:

1. A dissolvable microneedle array for transdermal insertion into a patient comprising:

one or more bioactive components;

- a base portion; and
- a plurality of microneedles extending from the base portion, the plurality of microneedles comprising a top half and a bottom half
- wherein the one or more bioactive components are concentrated in the top half of the microneedles,
- wherein the base portion and the plurality of microneedles comprise a plurality of layers of dissoluble biocompatible material,
- wherein the dissoluble biocompatible material define a shape of the plurality of microneedles, the one or more bioactive components are contained in the plurality of layers, and at least some of the plurality of layers that contain the one or more bioactive components are spatially separated from others of the plurality of layers that contain the one or more bioactive components.

2. The dissolvable microneedle array of claim 1, wherein the base portion is substantially formed without any bioactive components contained therein.

3. The dissolvable microneedle array of claim **2**, wherein the plurality of microneedles have a first cross-sectional dimension at an area of a top portion, a second cross-sectional dimension at an area of a bottom portion, and a third cross-sectional dimension at an area of an intermediate portion, wherein the third cross-sectional dimension is greater than the first and second cross-sectional dimensions.

4. The dissolvable microneedle array of claim **3**, wherein each microneedle generally tapers to a point above the intermediate portion and each microneedle generally tapers to a smaller cross-sectional dimension below the intermediate portion.

5. The dissolvable microneedle array of claim **1**, wherein the dissoluble biocompatible material is carboxymethylcel-lulose.

6. The dissolvable microneedle array of claim 2, wherein the one or more bioactive component comprises at least two different bioactive components.

7. The dissolvable microneedle array of claim 6, wherein the at least two different bioactive components are selected

from the group consisting of a chemotherapeutic agent, an adjuvant, and a chemo attractant for a cancer chemo immunotherapy application.

8. The dissolvable microneedle array of claim **6**, wherein the one or more bioactive component comprises an antigen 5 and an adjuvant for a vaccine application.

9. The dissolvable microneedle array of claim **2**, wherein the one or more bioactive component comprises at least one viral vector.

10. The dissolvable microneedle array of claim **9**, wherein 10 the at least one viral vector comprises an adenovector.

11. The dissolvable microneedle array of claim **1**, wherein the one or more bioactive component comprises doxorubicin.

12. The dissolvable microneedle array of claim **1**, wherein 15 the spatially separated layers of the one or more bioactive components comprise different active components.

13. The dissolvable microneedle array of claim **1**, wherein the spatially separated layers of the one or more bioactive components comprise different amounts of the same bioac- 20 tive component.

14. The dissolvable microneedle array of claim 1, whereinthe spatially separated layers of the one or more bioactivecomponents comprise different concentrations of the samebioactive component.25

* * * * *